

**Specification Amendments:**

Please amend the specification as indicated:

Please add the following paragraphs to the "SUMMARY OF THE INVENTION" section at a location to begin on page 8, line 12 and to end prior to the "BRIEF DESCRIPTION OF THE DRAWINGS" section:

A bioactive artificial sintered composition for providing a morphology capable of consistently supporting bone cell activity thereon, said composition comprising stabilized calcium phosphate phases developed by the conversion of a hydroxyapatite substance in the presence of stabilizing entities at sintering temperatures into insolubilized and stabilized tricalcium phosphate, wherein said calcium phosphate phases are in a ratio of 50:50 to 20:80 for hydroxyapatite to alpha tricalcium phosphate.

A process for stabilizing an artificial sintered composition of calcium phosphate phases having a morphology suitable for supporting bone cell activity thereon, said process comprising converting a hydroxyapatite substance into primarily alpha tricalcium phosphate by sintering, and providing stabilizing entities which stabilize and insolubilize the formed alpha tricalcium phosphate within the phosphate phases, wherein said calcium phosphate phases are in a ratio of 50:50 to 20:80 for the ratio of hydroxyapatite to alpha tricalcium phosphate.